

Data sheet EN Cu-DHP/CW024A – Rolled products 99,90 % pure copper Alumeco A/S		Internal alloy name: CW024A International alloy name: EN Cu-DHP DIN-Werkstoff no.: 2.0090 Alloy type: Electrical conducting Revision date: 11-01-2021																									
Main usage - Electrical - Architecture - Building - Consumer - Industrial	Main properties - It has excellent welding and soldering properties - It can be deformed excellent, either hot or cold	Important norms and literature Rolled products EN1652: Copper and copper alloys - Plate, sheet, strip and circles for general purposes. EN1172:2011 COPPER AND COPPER ALLOYS - SHEET AND STRIP FOR BUILDING PURPOSES																									
Chemical composition (%) DIN EN1652 & EN1172:2011 <table><tr><td>Cu</td><td>P</td><td>Each</td><td>Other elements together</td></tr><tr><td>99.90</td><td>0,015 – 0,040</td><td>-</td><td>-</td></tr></table>				Cu	P	Each	Other elements together	99.90	0,015 – 0,040	-	-																
Cu	P	Each	Other elements together																								
99.90	0,015 – 0,040	-	-																								
Typical mechanical properties DIN EN1652 (General Purposes) <table><tr><td>Material condition</td><td>Thickness range (mm)</td><td>Rm MPa</td><td>Rp_{0,2} MPa</td><td>A_{50mm} for thicknesses up to 2,5mm %</td><td>A for thickness up to 2,5mm %</td><td>Hardness HBW</td><td>Hardness HV</td></tr><tr><td>R220 (soft)</td><td>0,2 - 5</td><td>220-260</td><td>Max. 140</td><td>33</td><td>42</td><td>-</td><td>-</td></tr><tr><td>R240(1/2 hard)</td><td>0,2 – 15</td><td>240-300</td><td>Min. 180</td><td>8</td><td>15</td><td>-</td><td>-</td></tr></table>				Material condition	Thickness range (mm)	Rm MPa	Rp _{0,2} MPa	A _{50mm} for thicknesses up to 2,5mm %	A for thickness up to 2,5mm %	Hardness HBW	Hardness HV	R220 (soft)	0,2 - 5	220-260	Max. 140	33	42	-	-	R240(1/2 hard)	0,2 – 15	240-300	Min. 180	8	15	-	-
Material condition	Thickness range (mm)	Rm MPa	Rp _{0,2} MPa	A _{50mm} for thicknesses up to 2,5mm %	A for thickness up to 2,5mm %	Hardness HBW	Hardness HV																				
R220 (soft)	0,2 - 5	220-260	Max. 140	33	42	-	-																				
R240(1/2 hard)	0,2 – 15	240-300	Min. 180	8	15	-	-																				
Typical mechanical properties DIN EN1172:2011 (Building Purposes) <table><tr><td>Material condition</td><td>Rm MPa</td><td>Rp_{0,2} MPa</td><td>A_{50mm} %</td><td>Hardness HBW</td><td>Hardness HV</td></tr><tr><td>R220 (soft)</td><td>220-260</td><td>Max. 140</td><td>33</td><td>-</td><td>-</td></tr><tr><td>R240(1/2 hard)</td><td>240-300</td><td>Min. 140</td><td>8</td><td>-</td><td>-</td></tr></table>				Material condition	Rm MPa	Rp _{0,2} MPa	A _{50mm} %	Hardness HBW	Hardness HV	R220 (soft)	220-260	Max. 140	33	-	-	R240(1/2 hard)	240-300	Min. 140	8	-	-						
Material condition	Rm MPa	Rp _{0,2} MPa	A _{50mm} %	Hardness HBW	Hardness HV																						
R220 (soft)	220-260	Max. 140	33	-	-																						
R240(1/2 hard)	240-300	Min. 140	8	-	-																						
Physical properties <table><tr><td>Density (20 °C) g cm⁻³</td><td>Solidification range °C</td><td>Electrical conductivity %IACS</td><td>Thermal conductivity (20 °C) W m⁻¹ K⁻¹</td><td>Thermal expansion (20-300 °C) μm m⁻¹ K⁻¹</td><td>Annealing temperature °C</td><td>E - modulus (20 °C) N mm⁻²</td></tr><tr><td>9,0</td><td>1030</td><td>85</td><td>340</td><td>17</td><td></td><td>-</td></tr></table>				Density (20 °C) g cm ⁻³	Solidification range °C	Electrical conductivity %IACS	Thermal conductivity (20 °C) W m ⁻¹ K ⁻¹	Thermal expansion (20-300 °C) μm m ⁻¹ K ⁻¹	Annealing temperature °C	E - modulus (20 °C) N mm ⁻²	9,0	1030	85	340	17		-										
Density (20 °C) g cm ⁻³	Solidification range °C	Electrical conductivity %IACS	Thermal conductivity (20 °C) W m ⁻¹ K ⁻¹	Thermal expansion (20-300 °C) μm m ⁻¹ K ⁻¹	Annealing temperature °C	E - modulus (20 °C) N mm ⁻²																					
9,0	1030	85	340	17		-																					
Properties and information Fabrication Properties <table><tr><td>Hot Formability</td><td>Good</td></tr><tr><td>Cold Formability</td><td>Excellent</td></tr></table> Joining Methods <table><tr><td>Soldering</td><td>Excellent</td></tr><tr><td>Brazing</td><td>Excellent</td></tr><tr><td>Oxy-acetylene welding</td><td>Good</td></tr><tr><td>Gas-shielded arc welding</td><td>Excellent</td></tr></table>				Hot Formability	Good	Cold Formability	Excellent	Soldering	Excellent	Brazing	Excellent	Oxy-acetylene welding	Good	Gas-shielded arc welding	Excellent												
Hot Formability	Good																										
Cold Formability	Excellent																										
Soldering	Excellent																										
Brazing	Excellent																										
Oxy-acetylene welding	Good																										
Gas-shielded arc welding	Excellent																										