

Technical Data	
Material of face sheets (outer face)	TECU® Patina (Cu-DHP EN 1172)
Material of face sheets (inner face)	TECU® Classic (Cu-DHP EN 1172)
Thickness of the composite sheet [mm]	4.0
Material thickness (outer face) [mm]	0.3
Material thickness (inner face) [mm]	0.3
Core thickness [mm]	3.4
Total mass of the composite material [kg/ m ²]	10.9

Technical Properties	
Section modulus W [cm ³ / m]	1.03
Flexural Rigidity EJ [kNcm ² / m]	3900

Physical Properties of the face sheets	
Tensile strength (R _m) [N/ mm ²]	min. 240
Proof Strength (R _{p0.2}) [N/ mm ²]	min. 180
Elongation (A _{50mm}) [%]	min. 8
coefficient of expansion	1,7 mm/m Δ T 100 K

To be read in conjunction with KME document "Important instructions for Storage, Application and Processing of TECU®_bond".

© = KME Germany AG & Co. KG

The technical information contained herein is correct and corresponds to the state-of-art at the time of printing.

Although all due care and attention has been taken, we cannot accept liability for the content.

KME Germany AG & Co. KG

Architectural Solutions

Klosterstraße 29, 49074 Osnabrück, Germany

Tel.: +49 (0) 541 / 321-2000

Fax: +49 (0) 541 / 321-2111

www.kme.com/tecu, info-tecu@kme.com